



PFA HAMPLUS Product Data Sheet

Product Codes: 02.002.09.00 (clear), 02.102.09.00 (colors)

- Reprocessed PFA offered in: Clear, Dark Clear, Black, Blue, Brown, Grey, Green, MIX, Orange, Red, White, and Yellow.
- Customer specified MFR within range of 4-5
- Offered from FRL inventory as available.

TYPICAL PROPERTIES

| PROPERTY | METHOD ASTM-NORM | UNIT | TYPICAL VALUE |
|--------------------------------|---------------------|----------|-------------------------------|
| Melt Flow Rate (MFR) | D 2116 | g/10 min | 4-5 |
| Specific Gravity | D 792 | | 2.12 - 2.17 |
| Color | | | Customer Specified |
| Tensile Strength | D 3307 | Mpa | Min 20 |
| Elongation at Break | D 638 | % | Min 300 |
| Melting Point | D 2116 | °C | 305 +/- 10 |
| Continuous Service Temperature | - | °C | 260 |
| Pellet Configuration | | | Strand Cut |
| Package | | | Poly Lined Gaylord or Drum |
| RoHS/REACH Compliance | | | Compliant |

Fluoropolymer Resources, LLC and Fluoropolymer Resources, Inc., makes no representations, warranties, claims, or guarantees of any kind with respect to the information contained in this document, about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Information may not provide reliable indicators of properties obtained or obtainable by end users and processors. No representations, warranties, claims, or guarantee is made with respect to the suitability of these products for your processes or end use application. Responsibility remains with you to qualify these products as satisfactory to you for use in your processes and end product applications. This data sheet does not give or imply permission to practice any patented invention without the permission of the patent owner.

FRLUSA.COM • Phone: 860-423-7622 • Fax: 860-423-8366 • Email: info@friusa.net

6 Industrial Park Road, North Windham, CT 06256